



PROMOSOLV[™] 70IS

REMOVAL OF FLUX RESIDUES VAPOR PHASE PROCESS FOR HUMID ENVIRONMENTS

BENEFITS

PROMOSOLV 70IS is developed as a drop-in replacement for trichlorethylene, NPB and other solvent. While reducing substantially the HSE impact, the defluxing power is at an equivalent level.

Due to its formulation with isopropanol it is less prone to water absorption compared with formulations with ethanol, which makes the product more suitable in high humidity environments.

It is dedicated for removing reflowed flux residues and other contaminants on PCBA's, power modules, lead frames, BGA's, PoP, SIP applications or LED assemblies. Its low surface tension allows very well cleaning and rinsing under low stand-off components and difficult to reach spaces. It has very good compatible with all metals, including very sensitive ones and also with most plastics & elastomers, however recommended to validate before use.

PROMOSOLV 70IS is formulated with safety in mind. Its composition gives excellent flammability suppression properties, which provides a very high stability when used in an equipment. Some products in the market may loose their flammability suppression compound due to evaporation when used in an equipment.

PERFORMANCE	 Thermally and chemically stable in use The very low surface tension allows deep rinsing under low stand-off components Short cleaning, rinsing and drying times Stable process in humid environments
COST	 Continuous recycling in equipment for a long bath-life Can be returned for recycling and re-use The relative high boiling point reduces risk of solvent drag, so limiting consumption
HSE	 Very low toxicity Low global Warming Potential (GWP) & no Ozon depletion potential (ODP) Non-flammable & no flashpoint

SPECIFICATIONS

SPECIFICATIONS	VALUES	METHODS
Aspect	Colorless, clear	Visual
Purity (% weight)	>99.5	Internal / MO.SB.10033
Isopropanol (% weight)	<3	Internal / MO.SB.10033

CHARACTERISTICS

CHARACTERISTICS	VALUES	
Boiling point (°C/°F)	43°C/109°F	
Surface tension (dynes / cm)	14	
Flash point	None	
Density (g/cm³)	1,28	
Dynamic viscosity (mPa.s)	0.50	
Vapor pressure (kPa)	65	

PDS2024-02 ENv1

PROCESS RECOMMENDATION

The best process will depend on factors such as operating conditions, equipment, desired cleaning time and the nature of contaminants. Our team is ready to advise you.

- Do not remove parts too quick out of the drying zone to prevent unwanted loss of solvent.
- Compatibility report with different materials is available on request.
- For improved cleanability in the presence of stubborn flux residues, consider incorporating the Promosolv AD70 additive.
- It's recommended to work with a siliporite filter to separate water from the condensation loop.

PROCESS EXAMPLE

Vapor phase process

CLEANING

PROMOSOLV 70IS Temp: 38°C 100°F US: optional Time: 2-5 min

RINSING

DRYING ZONE Conc: 100% 70IS vapor Temp: 43°C/109°F Time: 5-60 sec **DRYING**

PACKAGING, STORAGE & SHELF LIFE

- Keep products in closed original packaging and store at room temperature.
- Shelf life is minimum 5 years from production date when kept in recommended conditions.
- PROMOSOLV 70IS is a azeotropic-like formulation which guarantees a safe use & storage.

AVAILABLE PACKAGING



Please verify the packaging details, including volume and availability, with your sales representative, as they may vary depending on the production facility where the product is manufactured.

HEALTH, SAFETY & ENVIRONMENT

PROMOSOLV 70IS is NOT a GREENWAY product. Although fully in line with safety & environmental regulations, this product doesn't match our strict criteria to be labelled as a Greenway product More info on our Greenway concept via this link.



LOOKING FOR A MORE SUSTAINABLE SOLUTION?

GREENWAY ALTERNATIVE

We currently don't have a Greenway alternative but our target is to develop one in the near future. In case you want us to prioritize the development of a Greenway alternative, do not hesitate to contact us.

PROPERTIES	PROMOSOLV 70IS
Ozone Depleting Potential (ODP)	0.00
Global Warming Potential (GWP)	93
VOC	yes
Flashpoint	no

Contains no Reach Substances (on Candidate list, Annex XIV & XVII) / Contains no persistent organic pollutant (EC 850/2004) / Contains no Import/Export Hazardous substances (EU 649/2012).

Used polluted product can be returned to us for recycling if regulations permit. Please contact your local sales contact for more details on our **ECOPROGRAM**.

Please refer always to the Safety Data Sheet (SDS or MSDS) prior to use. Our SDS can be downloaded at www.guickfds.com. We will request to provide your email address, so we can automatically send you a new version of the SDS when a future update would occur.



PROMOSOLV 70IS PDS2024-02 ENv1

TECHNICAL SUPPORT & FREE-OF-CHARGE TESTING

Inventec has a worldwide dedicated Technical Support team to help you along the various stages of our cooperation.

Depending on your request, we provide online or onsite support

- to select the right product based on your specific needs.
- to assist you in your product qualification process.
- to guide you with the initial set up of your process at all your worldwide manufacturing facilities.
- to provide fast response on technical issues which could occur at any time during mass production.

Customers are also welcome in our CLEANING CENTERS to see the process in action and to get convinced by our solutions. We cover water- and solvent based processes.

Inventec is unique in the world by developing not only cleaning materials but also soldering and coating solutions. These materials are very closely linked with each other from a process point of view. Talking to our Technical Team, who understands very well these 3 different product groups, will help you greatly to overcome technical challenges within your overall process.

Contact our technical support via contact@inventec.dehon.com or your local sales representative.

ABOUT INVENTEC

Inventec is a global provider of SOLDERING, CLEANING, COATING, COOLING materials for Electronic, Semiconductor and Industrial applications. For over 60 years we have shown leadership in innovation by putting HEALTH IMPACT, SUSTAINABILITY and RELIABILITY at the core of our product development.

With ISO 9001 & 14001 production sites in France, Switzerland, USA, Mexico, Malaysia and China we can guarantee a smooth and cost-effective supply chain.

We supply to many industries but the excellent performance of our products in applications which demand high reliability, leads us to focus especially on the AUTOMOTIVE, AEROSPACE, SEMICONDUCTOR, ENERGY and MEDICAL industry.

www.inventec.dehon.com



SOLDERING CLEANING COATING COOLING

In accordance with the Annex II of Directive 2011/65/UE (RoHS), including its amendments, we certify that this product does not contains quantities above 0.1% of Hg, Pb, Cr VI, PBB, PBDE, DEHP, BBP, DBP, DIBP and above 0.01% of Cd

This data is based on information that the manufacturer believes to be reliable and offered in good faith. In no event will INVENTEC PERFORMANCE CHEMICALS be responsible for special, incidental and consequential damages. The user is responsible to the Administrative Authorities (regulations for the protection of the Environment) for the conformity of his installation.

Inventec Performance Chemicals – 26 rue de Coulons. 94360 Bry-sur-Marne, France Limited company with capital of 600 000€ - 964 500 706 RCS Créteil

